



TALLICIN® 4600

Inhibited Metal Catalyst for Moisture-cure and 2K Polyurethanes

TYPICAL CHARACTERISTICS

Appearance	Light, Clear Liquid
Weight Per Gallon, Lbs	8.15
Flash Point, °C (CC)	34
Odor	Sweet Odor

Tallicin® 4600 is an organotin compound recommended as a general purpose cure promoter for moisture-cure and 2K polyurethane systems. Tallicin® 4600 is used with polyester, polyether, and polyacrylate polyols.

APPLICATIONS

Tallicin® 4600 can be used to promote curing of both moisture-cured and 2K polyurethane systems. In addition, Tallicin® 4600 can be used to increase working time in a polyaspartic coating when incorporated into the polyaspartic amine of a 2K coating system.

FEATURES

Extends the working time of polyurethane and polyaspartic coatings formulations. Provides a stabilized organotin compound catalyst without significantly affecting the through-cure.

PROUDCT USES (For professional use only. Not intended for retail sales.)

The proper use level will depend on the formulation employed, but a use level of Tallicin® 4600 in the range of 0.05% to 0.25% of the finished product is generally effective. The appropriate level of addition for Tallicin® 4600 must be evaluated thoroughly for commercial use.

SAFETY, STORAGE, AND HANDLING

Consult MSDS before use. Store Tallicin® 4600 in tightly sealed containers. Prevent contact with moisture and excess humidity. Once opened, any remaining Tallicin® 4600 in the container is best stored under dry nitrogen blanketing. Store, transfer, and handle under a nitrogen blanket. Replace damaged gaskets on drums or totes. Keep storage temperatures at 15°C - 40°C (59°F - 104°F). Shelf life of Tallicin® 4600 is 12 months from date product is shipped by Pflaumer and then maintained in original closed containers and stored in proper storage conditions at 25°C (75°F). For repackaging, use containers that will prevent moisture contamination.

OTHER PFLAUMER PRODUCTS FOR THE FORMULATOR

Pflaumer offers other products for formulating 2K coatings:

The information contained herein is to the best of our knowledge true and accurate and any suggestions are made without guarantee, express or implied, since the conditions of use are beyond our control. Pflaumer Brothers, Inc. disclaims any liability incurred in connection with the use of these data or suggestions.

Terachem ® 53-Colorants	37 Ready-to-use pigment dispersions for 2K polyurethanes and polyaspartics, including color packs for on-site use
Teracure ® Aliphatic Polyisocyanates	Complete line of HDI-based trimer isocyanates
Teraspartic ® Polyaspartic Amines	For slow, medium, and fast curing
Terachem ®53-2242	Anti-sag additive for 2K polyaspartics
Tallicin ®1500	Flow and leveling modifier
Tallicin ®3000	Pot life extender for trimer-type isocyanates used in 2K polyurethanes
Tallicin ®4000	Bubble-release, agent and flow/leveling modifier for high-solids polyurethanes
Tallicin ® 4040	Bubble-release, flow and leveling modifier for solvent-free polyaspartics and polyurethanes
Tallicin ®4600	Stabilized Tin Catalyst for Polyurethanes

CONTAINER SIZES

5 Gallon Pail (37.5 Lb/17 Kg)

55 Gallon Drum (441 Lb/200 Kg)

The information contained herein is to the best of our knowledge true and accurate and any suggestions are made without guarantee, express or implied, since the conditions of use are beyond our control. Pflaumer Brothers, Inc. disclaims any liability incurred in connection with the use of these data or suggestions.