

D

Н

Е

1008 WHITEHEAD ROAD EXTENSION | EWING, NEW JERSEY 08638 | P: 609-883-4610 | WWW.PFLAUMER.COM

# **TERAMINE<sup>®</sup> 890 HARDENER**

Medium-Cure, Low-Viscosity Hardener for Epoxies

## **TYPICAL CHARACTERISTICS**

Н

C

Ν

С

A

| Appearance .           | Clear Liquid |
|------------------------|--------------|
| Weight Per Gallon, Lbs | 8.60 ± 0.1   |
| Flash Point (TCC)      | >200° C      |
| Equivalent Weight      | 89           |
| NVW, %                 | 100 ± 0.1    |
| Viscosity, cps         | 100-300      |

#### COMPATIBILITY

Teramine<sup>®</sup> 890 is a unique cycloaliphatic amine hardener based on PACM for medium-cure epoxy-based coatings. The product is designed to cure Bis A and Bis F epoxies, as well as Bis A and Bis F epoxies modified with reactive diluents and non-reactive diluents. The product is recommended for use in light-tints and clear topcoats.

### **APPLICATIONS**

Teramine® 890 offers a viscosity of about 200 cps and promotes good flow and leveling characteristics for commercial and industrial floor coating applications. Epoxy coatings

based on Teramine® 890 can be applied by conventional spray, roller or brush. The

coatings provide excellent chemical resistance for pipe, tank, and container

The information contained herein is to the best of our knowledge true and accurate and any suggestions are made without guarantee, express or implied, since the conditions of use are beyond our control. Pflaumer Brothers, Inc. disclaims any liability incurred in connection with the use of these data or suggestions.

applications, as well as self-leveling floor coatings.

Epoxy coatings formulated with Teramine® 890 show high gloss, low color, good color stability, and excellent overall appearance.

#### FEATURES

Good Color and Overall Appearance with High Gloss

**Excellent Chemical Resistance** 

Low Viscosity

# PROUDUCT USES (For professional use only. Not intended for retail sales.)

Suggested mix ratio with standard Bis A epoxy resins (EEW 188) is 45.

### **CONTAINER SIZES**

5 Gallon Pail and 55 Gallon Drum.

The information contained herein is to the best of our knowledge true and accurate and any suggestions are made without guarantee, express or implied, since the conditions of use are beyond our control. Pflaumer Brothers, Inc. disclaims any liability incurred in connection with the use of these data or suggestions.