



TERAMINE® 910 HARDENER

Medium-Cure, Low-Viscosity Hardener for Epoxies

TYPICAL CHARACTERISTICS

Appearance .	Clear Liquid
Weight Per Gallon, Lbs	8.60 ± 0.1
Flash Point (TCC)	>200° C
Equivalent Weight	91
NVW, %	100 ± 0.1
Viscosity, cps	100-300

COMPATIBILITY

Teramine® 910 is a unique cycloaliphatic amine hardener based on PACM for medium-cure epoxy-based coatings. The product is designed to cure Bis A and Bis F epoxies, as well as Bis A and Bis F epoxies modified with reactive diluents and non-reactive diluents. The product is recommended for use in light-tints and clear topcoats.

APPLICATIONS

Teramine® 910 offers a viscosity of about 200 cps and promotes good flow and leveling characteristics for commercial and industrial floor coating applications. Epoxy coatings based on Teramine® 91 can be applied by conventional spray, roller or brush. The coatings provide excellent chemical resistance for pipe, tank, and container applications, as well as self-leveling floor coatings.

The information contained herein is to the best of our knowledge true and accurate and any suggestions are made without guarantee, express or implied, since the conditions of use are beyond our control. Pflaumer Brothers, Inc. disclaims any liability incurred in connection with the use of these data or suggestions.

Epoxy coatings formulated with Teramine® 910 show high gloss, low color, good color stability, and excellent overall appearance.

FEATURES

Good Color and Overall Appearance with High Gloss

Excellent Chemical Resistance

Low Viscosity

PROUDUCT USES (For professional use only. Not intended for retail sales.)

Suggested mix ratio with standard Bis A epoxy resins (EEW 188) is 45.

CONTAINER SIZES

5 Gallon Pail and 55 Gallon Drum.

The information contained herein is to the best of our knowledge true and accurate and any suggestions are made without guarantee, express or implied, since the conditions of use are beyond our control. Pflaumer Brothers, Inc. disclaims any liability incurred in connection with the use of these data or suggestions.